


In-House System for Applying
Solder Resist Masks and Assembly Layouts
LPKF ProMask and LPKF ProLegend





Two Usecases, One Solution

For years LPKF ProtoMat milling plotters have delivered excellent results in the production of printed circuit boards. LPKF offers two methods for professional surface finishing: solder resist with LPKF ProMask and assembly prints with LPKF ProLegend.

Solder Resist Masks and Assembly Print for In-House Prototyping

Solder resist is a fundamental requirement for soldering certainty – especially for SMT. Professional quality solder resist masks can quickly and effectively be applied to structured PCBs using the LPKF ProMask.

The solder resist mask is printed onto a transparency from the CAD program, transferred onto the PCB, and developed. In four simple steps the structured PCB is given a perfect surface finish for soldering without short circuits.

Assembly print uses a similar process. ProMask and ProLegend include all the tools and materials required for perfect results.

LPKF ProMask and LPKF ProLegend are essential tools for quick, easy and inexpensive PCB prototyping or small batches. A photo-optical exposure process transfers all structures or legends onto the PCB in just a few steps.


Benefits of LPKF ProMask:

- Quick, easy and cost-effective
- Clean electric insulation
- Protects against corrosion and oxidation

Benefits of LPKF ProLegend:

- High adhesion when using cleaners
- Simple process similar to LPKF ProMask
- Minimum character height of 2 mm (75 mil)

- Four simple steps
- Compact, quick and easy
- Effective soldering
- Professional legend



Application sample from a small batch, machined with LPKF ProMask

LPKF ProMask and ProLegend Provide Professional Finishing in Four Simple Steps:



1. Print photo template

The photo template with the desired layout is printed onto a transparency using LPKF CircuitPro and a standard laser printer.



2. Apply paint

Mix the solder resist from the pre-proportioned paint and hardener. Apply the solder resist onto the structured PCB with the included roller. The PCB is then pre-dried in a convection oven for 10 minutes.



3. Expose photo template

Position the photo template on the PCB and place both in the UV-exposer. Activate the laser setter for 30 seconds. Remove the PCB and remove the photo template.



4. Develop and harden solder resist mask

Prepare the developing bath with the developing powder and hot water. Use a brush to release the unexposed solder resist in the developing bath. The solder resist is then hardened and cleaned in a convection oven for 30 minutes. A powder pH-conditioner then neutralizes all chemical components for eco-friendly disposal.

Technical Specifications	LPKF ProMask	LPKF ProLegend
Part no.	117072	117584
Max. material size	229 mm x 305 mm (9" x 12")	
Max. layout area of image exposer	240 mm x 340 mm (9.5" x 13")	
Processing time	Approx. 60 min/cycle	
Pad separation	≥0.5 mm (20 mil) fine pitch	
Adhesive strength	Class H and T, test method: IPC-SM-840 C, item 3.5.2.1	
Solder bath resistance	20 s at 265 °C (509 °F), test method: IPC-SM-840 C, item 3.7.2 10 s at 288 °C (550 °F), test method: MIL-P 55 110 D 20 s at 288 °C (550 °F), test method: UL 94 (lead-free)	
Surface resistance	2 x 10 exp 14 Ω, test method: VDE 0303, Part 30, DIN IEC 93	
Moisture resistance and isolation resistance	Class H and T, test method: IPC-SM-840 C, item 3.9.1	
Solving/cleaning agent resistance	IPC-SM-840 C, item 3.9.1 (10 percent alkaline cleaner, Isopropanol, monoethanolamine)	
Minimum capital height	2.0 mm (with 1 200 dpi laser printer)	
Minimum capital strength	0.1 mm (with 1 200 dpi laser printer)	
Hardware requirements	Min. 600 dpi laser printer	
Software requirements	LPKF CircuitCAM 5.1 (or higher) or LPKF CircuitPro	

Technical specifications subject to change.

Required for Processing:



Worldwide (LPKF Headquarters)

LPKF Laser & Electronics AG Osteriede 7 30827 Garbsen Germany
Phone +49 (5131) 7095-0 Fax +49 (5131) 7095-90 info@lpkf.com
www.lpkf.com

North / Central America

LPKF Laser & Electronics North America
Phone +1 (503) 454-4200 Fax +1 (503) 682-7151 sales@lpkfusa.com
www.lpkfusa.com

China

LPKF Tianjin Co., Ltd.
Phone +86 (22) 2378-5318 Fax +86 (22) 2378-5398 sales@lpkf.cn
www.lpkf.cn

LPKF Laser & Electronics AG sells and markets products and provides support in more than 50 countries. Find your local representative at www.lpkf.com.